

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

| | | |
|--|-----------|---|
| (51) International Patent Classification ⁶: C07D 291/06, B27K 3/34, C07D 419/04 | A1 | (11) International Publication Number: WO 95/06043 (43) International Publication Date: 2 March 1995 (02.03.95) |
| (21) International Application Number: PCT/US94/09702 (22) International Filing Date: 24 August 1994 (24.08.94) (30) Priority Data: 111,386 24 August 1993 (24.08.93) US (71) Applicants: UNIROYAL CHEMICAL COMPANY, INC. [US/US]; World Headquarters, Middlebury, CT 06749 (US). UNIROYAL CHEMICAL LTD./UNIROYAL CHEMICAL LTEE [CA/CA]; 25 Erb Street, Elmira, Ontario N3B 3A3 (CA). (72) Inventors: DAVIS, Robert, A.; 1100 Notch Road, Cheshire, CT 06410 (US). VALCKE, Alex, R., A.; Beulk 80, B-2275 Wechelderzande (BE). BROUWER, Walter, G.; 15 Hickory Street, Guelph, Ontario N1G 2X2 (CA). (74) Agent: REITENBACH, Daniel; Uniroyal Chemical Company, Inc., World Headquarters, Middlebury, CT 06749 (US). | | (81) Designated States: AM, AU, BB, BG, BR, BY, CA, CN, CZ, FI, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LT, LV, MD, MG, MN, MW, NO, NZ, PL, RO, RU, SD, SI, SK, TJ, TT, UA, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD). Published <i>With international search report.</i> |
| (54) Title: WOOD PRESERVATIVE OXATHIAZINES (57) Abstract The present invention provides certain 3-aryl-5,6-dihydro-1,4,2-oxathiazines and their oxides, useful for the long-term preservation of wood and composite wood materials against wood damaging and wood destroying materials. The present invention also provides compositions containing these 3-aryl-5,6-dihydro-1,4,2-oxathiazines and their oxides, and a suitable vehicle therefor. A method of preserving wood is also disclosed in which a fungicidally or bactericidally effective amount of the present 3-aryl-5,6-dihydro-1,4,2-oxathiazines and their oxides, are applied to the wood substrate to be protected. | | |

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

| | | | | | |
|----|--------------------------|----|--|----|--------------------------|
| AT | Austria | GB | United Kingdom | MR | Mauritania |
| AU | Australia | GE | Georgia | MW | Malawi |
| BB | Barbados | GN | Guinea | NE | Niger |
| BE | Belgium | GR | Greece | NL | Netherlands |
| BF | Burkina Faso | HU | Hungary | NO | Norway |
| BG | Bulgaria | IE | Ireland | NZ | New Zealand |
| BJ | Benin | IT | Italy | PL | Poland |
| BR | Brazil | JP | Japan | PT | Portugal |
| BY | Belarus | KE | Kenya | RO | Romania |
| CA | Canada | KG | Kyrgyzstan | RU | Russian Federation |
| CF | Central African Republic | KP | Democratic People's Republic of Korea | SD | Sudan |
| CG | Congo | KR | Republic of Korea | SE | Sweden |
| CH | Switzerland | KZ | Kazakhstan | SI | Slovenia |
| CI | Côte d'Ivoire | LI | Liechtenstein | SK | Slovakia |
| CM | Cameroon | LK | Sri Lanka | SN | Senegal |
| CN | China | LU | Luxembourg | TD | Chad |
| CS | Czechoslovakia | LV | Larvia | TG | Togo |
| CZ | Czech Republic | MC | Monaco | TJ | Tajikistan |
| DE | Germany | MD | Republic of Moldova | TT | Trinidad and Tobago |
| DK | Denmark | MG | Madagascar | UA | Ukraine |
| ES | Spain | ML | Mali | US | United States of America |
| FI | Finland | MN | Mongolia | UZ | Uzbekistan |
| FR | France | | | VN | Viet Nam |
| GA | Gabon | | | | |

WOOD PRESERVATIVE OXATHIAZINES

5 This is a continuation-in-part of U.S. application
Serial No. 08/111,386, filed on August 24, 1993.

BACKGROUND OF THE INVENTION

10 1. Field of the Invention

The present invention relates to a process for preserving wood and composite wood materials from wood damaging organisms, and compositions useful in such process.

15 This invention more specifically is directed to a class of 3-aryl-5,6-dihydro-1,4,2-oxathiazines and their oxides which are useful against such wood damaging organisms as bacteria, yeasts, and fungi.

20 This invention is also directed to novel 3-aryl-5,6-dihydro-1,4,2-oxathiazines and their oxides which are useful against such wood damaging organisms as bacteria, yeasts, and fungi.

25 2. Description of Related Art

The preservation of wood is a subject of great economic importance. For most purposes, untreated wood is entirely unsatisfactory. It will twist, warp, and crack as it dries; it cannot easily be glued or finished,

-2-

and it is subject to attack of fungi and/or insects. Properly prepared and preserved wood possesses strength and incompressibility while being flexible.

U.S. Patent 4,569,690 refers to various 3-aryl-5,
5 6-dihydro-1,4,2-oxathiazines and their oxides said to be useful as herbicides, plant fungicides, plant dessicants and defoliants. No mention is made of preserving wood materials from damaging organisms.

Chemical Abstracts 103(1):2144u refers to fungicides
10 containing phenyl-alpha-chloroacetamides said to be effective in industrial environments including paints, metal cutting fluids, and to prevent the growth of cellulose degrading fungus on treated wood.

Chemical Abstracts 102(16):133786g refers to
15 resistance to biological attack in wood treated with epoxides. U.S. Patent 4,562,185 refers to 1-oxo-3-azacyclopentane derivatives said to be useful as pesticides, especially systemic insecticides, effective against acarids and nematodes and showing residual activity on
20 wood and clay.

U.S. Patent 4,067,862 refers to a process for modification of polymeric materials with a nitrile sulfide. The modified polymers are said to have uses including decorative or protective coatings for wood.


25 World Patents Index 67-05105G/00 refers to fungicidal 2-mono substituted amino 1-azacycloalkene-1 compounds, said to have fungicidal activity in both plants and other organic materials including wood.

-3-

U.S. Patent 4,977,186 refers to wood preservative and soil treatment compositions containing carbamates.


SUMMARY OF THE INVENTION

5 This invention relates to a compound of the formula



10 wherein n is 0, 1 or 2; R^1 is hydrogen, C_1 - C_4 linear or branched alkyl, or benzyl; and
Q is:

(a)




15

wherein R^2 , R^3 and R^4 are, individually, hydrogen, alkyl, alkoxy, alkylthio, alkoxycarbonyl, halogen, trihalomethyl, cyano, acetyl, formyl, benzoyl, nitro, alkoxyaminomethyl, phenyl, or phenylaminocarbonyl,

20 wherein the alkyl or alkoxy moieties are all C_1 - C_4 , linear or branched, with the proviso that at least one of R^2 , R^3 or R^4 must be other than hydrogen;

(b)




25

wherein R^5 , R^6 and R^7 are, individually, hydrogen, C_1 - C_4 alkoxy, C_1 - C_4 alkylthio, halogen, trihalomethyl, cyano, acetyl, formyl, benzoyl, nitro, phenyl, or

-4-

phenylaminocarbonyl, with the proviso that at least one of R^5 , R^6 or R^7 must be other than hydrogen;

(c)




5

wherein R^8 , R^9 and R^{10} are, individually, hydroxyl, halo, C_1 - C_{12} alkyl, C_5 - C_6 cycloalkyl, trihalomethyl, phenyl, C_1 - C_5 alkoxy, C_1 - C_5 alkylthio, tetrahydropyranyloxy, phenoxy, (C_1 - C_4 alkyl)carbonyl, phenylcarbonyl, C_1 - C_4 alkylsulfinyl, C_1 - C_4 alkylsulfonyl, carboxy or its alkali metal salt, (C_1 - C_4 alkoxy)carbonyl, (C_1 - C_4 alkyl)aminocarbonyl, phenylaminocarbonyl, tolylaminocarbonyl, morpholinocarbonyl, amino, nitro, cyano, dioxolanyl, or (C_1 - C_4 alkoxy)iminomethyl; or

15

(d)



wherein X is oxygen or sulfur; Y is nitrogen, -CH-, or -C(C_1 - C_4 alkoxy)-; and R'' is hydrogen or C_1 - C_4 alkyl.

20

The compounds of the present invention are useful for the long-term preservation of wood and composite wood materials against wood damaging and wood destroying materials.


25

The present invention also provides methods useful for the long-term preservation of wood and composite wood materials against wood damaging and wood destroying materials. For the purpose of this invention, a

-5-

composite wood material is any product made from wood, including, but not limited to, plywood, pressed wood, chipboard, particle-board, wafer board, wood laminated material and the like.

5 In accordance with the present methods, a wood material is preserved by treatment with a fungicidally or bactericidally effective amount of an active agent represented by the formula below



wherein n is 0, 1 or 2; R¹ is hydrogen, C₁-C₄ linear or branched alkyl, or benzyl; and

15 R is:

(a) phenyl; naphthyl; phenyl substituted with 1-3 of the following substituents:

hydroxyl, halo, C₁-C₁₂ alkyl, C₅-C₆ cycloalkyl, trihalomethyl, phenyl, C₁-C₅ alkoxy, C₁-C₅ alkylthio, tetrahydropyranyloxy, phenoxy, (C₁-C₄ alkyl)carbonyl, 20 phenylcarbonyl, C₁-C₄ alkylsulfinyl, C₁-C₄ alkylsulfonyl, carboxy or its alkali metal salt, (C₁-C₄ alkoxy)carbonyl, (C₁-C₄ alkyl)aminocarbonyl, phenylaminocarbonyl, tolylaminocarbonyl, 25 morpholinocarbonyl, amino, nitro, cyano, dioxolanyl, or (C₁-C₄ alkoxy)iminomethyl; pyridinyl; thienyl, preferably when n is not 2; furanyl; or thienyl or furanyl substituted with 1 to 3 of the


-6-

following groups:

alkyl, alkoxy, alkylthio, alkoxycarbonyl, halogen, trihalomethyl, cyano, acetyl, benzoyl, nitro, formyl, alkoxyaminomethyl, phenyl, or phenylaminocarbonyl, wherein the alkyl or alkoxy moiety is C₁-C₄, linear or branched;

or

(b)



wherein X is oxygen or sulfur; Y is nitrogen, -CH-, or -C(C₁-C₄ alkoxy)-; and R'' is hydrogen or C₁-C₄ alkyl.

In further accordance with the present invention, there is provided a composition comprising a) a wood preservative amount of a compound of formula I or II, and b) a suitable carrier.

DETAILED DESCRIPTION OF THE INVENTION

A preferred embodiment of the compounds of this invention are those compounds of formula I wherein R¹ is hydrogen or C₁-C₄ alkyl; n is 1 or 2; R², R³ and R⁴ are, individually, hydrogen, C₁-C₄ alkyl, halo, (C₁-C₄ alkoxy)-carbonyl, or cyano, with the proviso that at least one of R², R³ and R⁴ must be other than hydrogen; R⁵, R⁶ and R⁷ are, individually, hydrogen, halo or cyano, with the proviso that at least one of R⁵, R⁶ and R⁷ must be other than hydrogen; R⁸, R⁹ and R¹⁰ are C₁-C₄ alkyl, C₁-C₄

-7-

alkoxy, nitro, halo, trihalomethyl, or (C₁-C₄ alkoxy)-carbonyl; X is sulfur; and R" is hydrogen.

More preferred are those compounds of formula I wherein R¹ is hydrogen; n is 1 or 2; R², R³ and R⁴ are, individually, hydrogen, methyl, ethyl, bromo, chloro, ethyl carboxylate, or cyano, with the proviso that at least one of R², R³ and R⁴ must be other than hydrogen; R⁵, R⁶ and R⁷ are, individually, hydrogen, bromo, chloro or cyano, with the proviso that at least one of R⁵, R⁶ and R⁷ must be other than hydrogen; R⁸, R⁹ and R¹⁰ are methyl, ethyl, nitro, fluoro, chloro, or trifluoromethyl.

In a preferred embodiment of the method of the present invention, the compounds of structure II are substituted with R¹ being hydrogen, n being one or two, and R has one or 2 of the following values:

phenyl, (C₁-C₆ alkyl)phenyl, halophenyl, dihalophenyl, biphenyl, (C₁-C₅ alkyloxy)phenyl, trihalomethylphenyl, nitrophenyl, phenyl substituted with (C₁-C₄ alkoxy)carbonyl, furanyl, furanyl substituted by ethyl carboxylate, cyano, chlorine, or bromine, thienyl, thienyl substituted with ethyl carboxylate, cyano, chlorine, or bromine, or (C₁-C₆ alkyl)nitrophenyl.

In a still further preferred embodiment of the method of this invention, R¹ is hydrogen, n is one or two, and R is represented by:


4-chlorophenyl, 3-nitrophenyl, 3,4-dichlorophenyl, 3-fluorophenyl, 2-thienyl, 4-methylphenyl, 3-trifluoromethylphenyl, 3-ethanonephenyl,

-8-

3,5-dichlorophenyl, 4-trifluoromethylphenyl,
3-methyl-4-nitrophenyl.

In another preferred embodiment of the method of
this invention, R¹ is hydrogen, and R is

5



wherein X is sulfur, Y is nitrogen or -CH-, and R'' is
hydrogen.

10

The compounds of formula I and II can be prepared
utilizing the procedures described in U.S. Patent
4,569,690, the disclosure of which is incorporated herein
by reference, or the procedures described in Examples 1-8
below. That patent discloses detailed examples of the
synthesis of several 3-aryl-5,6-dihydro-1,4,2-
oxathiazines and their oxides by two methods: one
utilizing aromatic aldehydes as starting materials and
one using arylcarbodithioate esters. Either method is
viable and may be understood by one skilled in the art of
organic chemical synthesis.

20

The compositions of this invention include a
suitable carrier. Generally, the carrier may be a liquid
vehicle for dissolving or suspending the active wood
preservative ingredient. The vehicle typically contains
at least one of a diluent, an emulsifier, and a wetting
agent.

25

In addition, the carrier may also include other

-9-

adjuvants conventionally employed in wood preserving compositions, such as organic binding agents, additional fungicides, insecticides, auxilliary solvents, processing additives, fixatives, plasticizers, UV-stabilizers or
5 stability enhancers, water soluble or water insoluble dyes, color pigments, siccatives, corrosion inhibitors, antisetling agents, anti-skinning agents, and the like.

The wood preservative composition is typically supplied as a preparation with the active ingredients
10 dissolved or dispersed in a liquid vehicle or carrier material, such that the active chemical ingredient(s) comprise from about 0.001% by weight up to about 10% by weight of the total composition. More generally, the active fungicidal or bactericidal ingredients will
15 comprise from about 0.1 to 5% by weight, and most often from about 1 to about 5% by weight. For most wood preservative applications, the liquid vehicle can constitute as little as 5% by weight of the preparation. The composition of the present invention can be provided
20 as a ready for use product in the form of aqueous solutions and dispersions, emulsions, aerosol preparations and the like or as a concentrate. The concentrate can be used as is, for example, as an additive for plywood glues, or can be diluted prior to
25 use with additional solvent or suspending agents.

The liquid vehicle is not a critical aspect of the present invention and any liquid that does not interfere with the bactericidal and fungicidal activities of the

-10-

active ingredients and which is compatible with wood preserving applications potentially can be used in the present invention. Suitable diluents for the liquid vehicle include water and organic solvents including aromatic hydrocarbons such as xylene, toluene, high aromatic petroleum distillates such as solvent naphtha, distilled tar oil and mixtures thereof, alcohols such as butanol, octanol, and glycols, vegetable and mineral oils, ketones such as acetone, petroleum fractions such as mineral spirits and kerosene and the like.

The diluent of the liquid vehicle generally comprises an organic solvent or solvent mixture. The liquid vehicle may contain at least one polar solvent, such as water, in admixture with an oily or oil-like low volatility organic solvent, such as the mixture of aromatic and aliphatic solvents found in white spirits, also commonly called mineral spirits.

Oily or oil-like or organic solvents useful in the present invention preferably have a flash point above 28°C and a boiling range, at atmospheric pressure, between about 130°C to 250°C while low-volatility organic solvents preferably have a flash point above about 55°C and a boiling range, at atmospheric pressure, between about 180°C to 350°C. The liquid vehicle is selected to enhance penetration of the active ingredients into the wood or wood product being treated.

An aerosol preparation according to the invention is obtained in the usual manner by incorporating the active

-11-

ingredients dissolved or suspended in a suitable solvent,
in a volatile liquid suitable for use as a propellant,
for example, the mixture of chlorine and fluorine
derivatives of methane and ethane commercially available
5 under the FREON trademark, or compressed air.

The balance of the composition may include
additional ingredients known to be useful in wood
preservatives and related products. Such ingredients
include organic binding agents, such as alkyd resins;
10 fixatives such as carboxymethylcellulose, polyvinyl
alcohol, paraffin and the like; co-solvents, such as
ethylglycol acetate and methoxypropyl acetate; and
plasticizers such as benzoic acid esters and phthalates,
for example, dibutyl phthalate, dioctyl phthalate, and
15 diodecyl phthalate. Optionally, dyes, color pigments,
corrosion inhibitors, chemical stabilizers or dryers such
as cobalt octate and cobalt naphthenate also may be
included depending on specific applications and user
preference.

20 The organic binding agent can be a chemically drying
organic binder-forming polymer or a physically drying
organic binder forming solids by solvent evaporation.
Alkyd resins are a suitable class of organic binding
agents; others will be recognized by those skilled in the
25 art. The organic binding agents may themselves be
supplied in a liquid vehicle, and in that case the
amounts referred to herein for the organic binder are on
a solids basis.

-12-

As mentioned above, such additional ingredients may include additional fungicides and insecticides. Suitable additional fungicides would be apparent to one skilled in the art, and will vary according to application.

- 5 Examples include those fungicides known to have wood preservation uses, such as azaconazole, dichlofluanid, acypetacs, propiconazole, imazalil, cyproconazole, hexaconazole, IPBC, isothiozalone, tolylfluanid, chlorotalonil, benzimidazoles, Cu-oxides and Cu-HDO.
- 10 Suitable insecticides would also be apparent depending upon application, and could include, for example, chlorpyrifos, cypermethrin, fenvalerate, isofenphos, permethrin, silafluofen, deltamethrin, cyfluthrin and imidachloprid. Such additional ingredients are not
- 15 essential to the practice of the present invention but are included in particular formulations to optimize overall effectiveness and ease of application. The specific examples of suitable constituents for a wood preservative preparation as enumerated above are not
- 20 meant to be limiting and a wide variety of other possible ingredients will be recognized to one skilled in the art. Similarly, the quantity of such ingredients in any formulation is not critical and can be used in an amount conventionally employed for products designed to be used
- 25 in wood preserving applications. Normally, the totally formulated compositions may contain from about 0.1% to 95% by weight, and more usually from about 1% to 50% by weight of these additional ingredients on a total solids

-13-

basis.

The wood preservative composition can be applied by any of the techniques known in the art including brushing, spraying, dipping, and the like. Generally, to
5 obtain an effective treatment, it should be efficient to apply between about 0.05 to 0.4 kilogram of the composition per square meter of wood surface area to be treated, which is equivalent to about 0.01 to 0.08 pound per square foot. An amount of about 0.1 to 0.2 kg/m², or
10 about 0.02 to 0.04 pound/square foot, is more typical.

The active ingredient may also be applied in the wood by methods known in the art. Such methods include vacuum pressure impregnation, injection and diffusion. Suitable dose ranges for these methods include from about
15 0.01 to about 6.0 Kg/m³ and preferably from about 0.5 to about 6 kg/m³, and more preferably from about 0.5 to about 1.5 kg/m³ of active ingredient in the treated wood.

The composition of the present invention can be prepared by mixing the various ingredients at a
20 temperature at which they are not adversely affected, which usually will be from about -5°C to 80°C, preferably at a temperature of from about 10°C to 45°C, and at a pressure of 450 mm Hg to 900 mm Hg, preferably at about 650 mm Hg to 850 mm Hg. Preparation conditions are not
25 critical. Equipment and methods conventionally employed in the manufacture of coating compositions may be advantageously employed.

The following examples are presented for

-14-

illustrative purposes and are not intended to limiting the scope of this invention in any manner.

The compounds listed in Table 1 were prepared utilizing the procedures described in U.S. Patent 4,569,690. The compounds listed in Tables 2, 3 and 4 were prepared utilizing the procedures described in Examples 1-9 below.

EXAMPLES

10

Example 1

1,4,2-Oxathiazine,3-(5-chloro-2-thienyl)-5,6-dihydro-(Compound #59)

15 Methyl 5-chloro-2-thiophenecarbodithioate (61.4g, 0.29 mol) was suspended in methanol (400 ml) with finely powdered hydroxylamine hydrochloride (25g). With stirring, triethylamine (50 ml) in methanol (50 ml) was added dropwise to the suspension, to produce a reaction mixture. During this addition, the reaction mixture was cooled to 5°C. Stirring of the reaction mixture was continued until an orange (from red) color developed in the reaction mixture. Additional triethylamine (100 ml) was then added at once, followed by 1,2-dibromoethane (20 ml). The resultant reaction mixture was then stirred overnight at ambient temperature. The reaction mixture was then refluxed with removal of solvent until a precipitate appeared. The reaction mixture was then cooled and water was added. The reaction mixture was

20

25

-15-

then filtered and the solid collected on the filter was recrystallized from ethanol to produce 3-(5-chloro-2-thienyl)-5,6-dihydro-1,4,2-oxathiazine (mp 74-77°C, 21.4g. Found C 38.5, H 2.94, N 6.45, $C_7H_6ClNOS_2$ requires C 38.27, H 2.73, N 6.38)

Example 2

3-(5-Chloro-2-thienyl)-5,6-dihydro-1,4,2-oxathiazine-4,4-dioxide (Compound #61)

3-(5-Chloro-2-thienyl)-5,6-dihydro-1,4,2-oxathiazine (12g, 0.055 mol) prepared in Example 1, in methylene chlorine (50 ml) and anhydrous magnesium sulphate (10g) in suspension, was stirred while m-chloroperoxybenzoic acid (34g, 50-60% material) in methylene chloride (250 ml), was added dropwise, to prepare a reaction mixture. The reaction mixture was allowed to warm to 30°C and after the dropwise addition was externally heated to 35°C for 10 hours by which time a negative starch/KI test was obtained. Unwanted m-chlorobenzoic acid was then removed from the reaction mixture by extraction with aqueous sodium bicarbonate. The remaining reaction mixture was washed with water, dried ($MgSO_4$) and evaporated to dryness. The resultant residue was chromatographed on 500g silica gel eluting with methylene chloride, to produce 3-(5-chloro-2-thienyl)-5,6-dihydro-1,4,2-oxathiazine-4,4-dioxide (mp 113-114°C, 14.3g, Found: C 33.27, H 2.33, N 5.55; $C_7H_6ClNO_3S_2$ requires C 33.40, H 2.39, N 5.57).

-16-

Example 3Synthesis of 3-(5-chloro-2-thienyl)-5,6-dihydro-1,4,2-oxathiazine-4-oxide (Compound #60)

5 3-(5-Chloro-2-thienyl)-5,6-dihydro-1,4,2-oxathiazine
(12.4g, 0.056 mol) prepared in Example 1, in methylene
chloride (50 ml), was stirred while m-chloroperoxybenzoic
acid (16.2g) in methylene chloride (250 ml), was added
dropwise, to prepare a reaction mixture. The reaction
10 mixture was allowed to warm to 30°C and after the
dropwise addition was externally heated to 35°C for 10
hours by which time a negative starch/KI test was
obtained. Unwanted m-chlorobenzoic acid was then removed
from the reaction mixture by extraction with aqueous
15 sodium bicarbonate. The remaining reaction mixture was
washed with water, dried (MgSO₄) and evaporated to
dryness. The resultant residue was chromatographed on
500g silica gel eluting with methylene chloride, to
produce 3-(5-chloro-2-thienyl)-5,6-dihydro-1,4,2-
20 oxathiazine-4-oxide (mp 102°C, 11.4g, Found: C 35.82,
H 2.56, N 5.89, C₇H₆ClNO₂S₂ requires C 35.67, H 2.55,
N 5.94.

Example 4

25 Synthesis of 1,4,2-oxathiazine, 5,6-dihydro-6-methyl-3-(2-thienyl)- (Compound #52)

Methyl-2-thiophenecarbodithioate (47g, 0.27 mol) in
methanol (250 ml) at 0-5°C, was stirred and treated with
30 powdered hydroxylamine hydrochloride (20g) and followed
by dropwise addition of triethylamine (50 ml) in methanol

-17-

(50 ml) over 2 hours, to prepare a reaction mixture. Additional hydroxylamine hydrochloride (5g) and triethylamine (10 ml) was added consecutively to the reaction mixture and after 45 minutes, the reaction mixture turned yellow (from red). 1,2-Dibromopropane (26 ml) was then added to the yellow reaction mixture, followed by addition of triethylamine (75 ml). The resultant new reaction mixture was refluxed for 4 hours and then left overnight at ambient temperature. The methanol was removed from the reaction mixture to leave a residue. Water was added to the residue which was then extracted into ethyl acetate, washed with dilute hydrochloric acid (2N, 100 ml), water, and dried (MgSO_4). The ethyl acetate was then removed to leave a brown oil which was crystallized with cyclohexane to produce two crops of 5,6-dihydro-6-methyl-3-(2-thienyl)-1,4,2-oxadiazine (11.7g and 3.7g, mp 70-72°C) Found: C 48.90, H 4.66, N 7.17, $\text{C}_8\text{H}_9\text{NOS}_2$ requires C 48.24, H 4.52, N 7.07

20 Example 5

Synthesis of 5,6-dihydro-6-methyl-3-(2-thienyl)-1,4,2-oxathiazine-4,4-dioxide (Compound #51)

The 5,6-dihydro-6-methyl-3-(2-thienyl)-1,4,2-oxathiazine produced in Example 4 above (2.8g, 0.013 mol), was oxidized with m-chloroperoxybenzoic acid (9.8g) as described in Example 1. Excess peroxide was destroyed with aqueous sodium bisulphite. Extraction produced 5,6-dihydro-6-methyl-3-(2-thienyl)-1,4,2-oxathiazine-

-18-

4,4,dioxide (from ethanol) (2.1g, mp 147-148°C). Found C 42.06, H 3.99, N 6.08, $C_8H_9NO_3S_2$ requires C 41.56, H 3.90, N 6.06.

5 Example 6

Synthesis of 5,6-dihydro-6-methyl-3-(2-thienyl)-1,4,2-oxathiazine-4-oxide (Compound #50)

10 The 5,6-dihydro-6-methyl-3-(2-thienyl)-1,4,2-oxadiazine produced in Example 4 above (2.8g, 0.013 mol), was oxidized with m-chloroperoxybenzoic acid (3.7g) as described in Example 1. The resultant product was recrystallized from ethanol to produce 5,6-dihydro-6-methyl-3-(2-thienyl)-1,4,2-oxathiazine-4-oxide (1.3g, mp
15 114-115°C). Found C 44.85, H 4.31, N 6.54, $C_8H_9NO_2S_2$ requires C 44.65, H 4.19, N 6.51.

Example 7

20 Synthesis of 5,6-dihydro-3-(2-benzothiazolyl)-1,4,2-oxathiazine (Compound #84)

25 Methyl 2-benzothiazolecarbodithioate (37g, 0.16 mol) was converted to 1,4,2-oxathiazine using hydroxylamine hydrochloride (13.2g) and triethylamine (33 ml) as described in Example 4. The ethyl acetate extract of the product was washed successively with diluted hydrochloric acid (2N), water, 5% sodium hydroxide and water. Evaporation of the solvent left a solid residue which was
30 recrystallized from ethanol/ethyl acetate to 5,6-dihydro-3-(2-benzothiazolyl)-1,4,2-oxathiazine (18.0g, mp 150-

-19-

151°C) Found C 50.68, H 3.27, N 11.78, $C_{10}H_8N_2OS_2$ requires C 50.85, H 3.39, N 11.80.

Example 8

5 Synthesis of 5,6-dihydro-3-(2-benzothiazolyl)-1,4,2-oxathiazine-4,4-dioxide (Compound #83)

The 5,6-dihydro-3-(2-benzothiazolyl)-1,4,2-oxathiazine produced in Example 7 (4.2g, 0.018 mol) was oxidized with m-chloroperoxybenzoic acid as described in
10 Example 5, to produce 5,6-dihydro-3-(2-benzothiazolyl)-1,4,2-oxathiazine 4,4-dioxide (3.7g, mp 226-227°C). Found C 44.59, H 3.01, N 10.31, $C_{10}H_8N_2O_3S_2$ requires C 44.78, H 2.99, N 10.45.

15 Example 9


Synthesis of 5,6-dihydro-3-(2-benzothiazolyl)-1,4,2-oxathiazine-4-oxide (Compound #85)

The 5,6-dihydro-3-(2-benzothiazolyl)-1,4,2-oxathiazine produced in Example 7 was oxidized as
20 described in Example 6 to produce 5,6-dihydro-3-(2-benzothiazolyl)-1,4,2-oxathiazine-4-oxide (2.3g, mp 192-195°C). Found
C 47.96, H 3.26, N 11.22, $C_{10}H_8N_2O_2S_2$ requires C 47.62,
25 H 3.17, N 11.11.

Tables 1-4 list representative compounds numbered 1-107.

- 20 -


TABLE I



| Compound # | n | R |
|------------|---|-------------------------|
| 1 | 1 | 4-chlorophenyl |
| 2 | 2 | 2,4-dichlorophenyl |
| 3 | 1 | 3-nitrophenyl |
| 4 | 1 | 3,4-dichlorophenyl |
| 5 | 2 | 2-methylphenyl |
| 6 | 1 | 3-fluorophenyl |
| 7 | 1 | 2-furanyl |
| 8 | 1 | 2-thienyl |
| 9 | 1 | 3-methoxyphenyl |
| 10 | 1 | 4-methylphenyl |
| 11 | 2 | 4-methylphenyl |
| 12 | 2 | 2-furanyl |
| 13 | 1 | 3-trifluoromethylphenyl |
| 14 | 1 | 4-ethanonephenyl |
| 15 | 1 | 2,6-dichlorophenyl |

- 21 -


TABLE I (CONT)



| Compound # | n | R |
|------------|---|------------------------------|
| 16 | 2 | 2,6-dichlorophenyl |
| 17 | 2 | phenyl |
| 18 | 2 | 4-chlorophenyl |
| 19 | 2 | 3,5-dichlorophenyl |
| 20 | 1 | 4-butoxyphenyl |
| 21 | 1 | 3,5-dichlorophenyl |
| 22 | 1 | 4-benzoic acid, ethyl ester |
| 23 | 2 | 3-chlorophenyl |
| 24 | 2 | 4-trifluoromethylphenyl |
| 25 | 1 | 4-trifluoromethylphenyl |
| 26 | 1 | 3-benzoic acid, methyl ester |
| 27 | 2 | 3-bromophenyl |
| 28 | 1 | 4-ethoxyphenyl |


- 22 -

TABLE 2



| CMPD # | R ¹ | R ² | R ³ | R ⁴ | X | n | M.P. (°C) |
|--------|-----------------|-----------------|---------------------------------|---|---|---|-----------|
| 29 | H | H | H | CO ₂ CH ₃ | O | 0 | 85-89 |
| 30 | H | H | H | CO ₂ CH ₃ | O | 2 | 126-129 |
| 31 | H | H | H | CO ₂ CH ₃ | O | 1 | 118-119 |
| 32 | H | CH ₃ | H | H | S | 0 | oil |
| 33 | H | CH ₃ | H | H | S | 1 | 73-75 |
| 34 | H | H | H | H | S | 2 | 99-101 |
| 35 | H | H | H | Br | S | 0 | 82-83 |
| 36 | H | H | H | Br | S | 1 | 113-114 |
| 37 | H | CH ₃ | H | H | S | 2 | 60-62 |
| 38 | H | H | H | Br | S | 2 | 118-119 |
| 39 | H | H | CO ₂ CH ₃ | CH ₃ | O | 0 | 87-88 |
| 40 | H | H | Br | H | S | 0 | 74-75 |
| 41 | H | H | Br | H | S | 1 | 169-173 |
| 42 | H | H | Br | H | S | 2 | 126-127 |
| 43 | H | H | CO ₂ CH ₃ | CH ₃ | O | 2 | 156-157 |
| 44 | H | H | CO ₂ CH ₃ | CH ₃ | O | 1 | 147-148 |
| 45 | H | H | CH ₃ | CO ₂ CH ₃ | S | 1 | 150-152 |
| 46 | H | H | CH ₃ | CO ₂ CH ₃ | S | 2 | 125-126 |
| 47 | H | H | H | CH ₃ | S | 0 | 62-63 |
| 48 | H | H | H | CH ₃ | S | 1 | 109-111 |
| 49 | H | H | H | CH ₃ | S | 2 | 101-102 |
| 50 | CH ₃ | H | H | H | S | 1 | 114-115 |
| 51 | CH ₃ | H | H | H | S | 2 | 147-148 |
| 52 | CH ₃ | H | H | H | S | 0 | 70-72 |
| 53 | H | H | H | CO ₂ CH ₂ CH ₃ | S | 0 | 68-69 |


TABLE 2 (CONT)



| CMPD # | R ¹ | R ² | R ³ | R ⁴ | X | n | M.P. (°C) |
|--------|----------------|----------------|-----------------------------------|---|---|---|-----------|
| 54 | H | H | H | CO ₂ CH ₂ CH ₃ | S | 1 | 109-110 |
| 55 | H | H | H | CO ₂ CH ₂ CH ₃ | S | 2 | 123-124 |
| 56 | H | H | H | CN | S | 0 | 136-137 |
| 57 | H | H | H | CN | S | 1 | 160-162 |
| 58 | H | H | H | CN | S | 2 | 153-155 |
| 59 | H | H | H | Cl | S | 0 | 74-77 |
| 60 | H | H | H | Cl | S | 1 | 102 |
| 61 | H | H | H | Cl | S | 2 | 113-114 |
| 62 | H | H | H | CHO | S | 0 | 48-49 |
| 63 | H | H | H | NO ₂ | S | 0 | 162-163 |
| 64 | H | H | H | NO ₂ | S | 1 | 186-188 |
| 65 | H | H | H | NO ₂ | S | 2 | 160-161 |
| 66 | H | H | H | CH=NOCH ₃ | S | 2 | 168-170 |
| 67 | H | H | H | C ₆ H ₅ | S | 0 | 100-103 |
| 68 | H | H | H | C ₆ H ₅ | S | 1 | 144-147 |
| 69 | H | H | H | C ₆ H ₅ | S | 2 | 95-98 |
| 70 | H | H | NO ₂ | C ₆ H ₅ | S | 0 | 140-145 |
| 71 | H | H | CH ₃ | Br | S | 0 | oil |
| 72 | H | H | CH ₃ | Br | S | 1 | 100-104 |
| 73 | H | H | Br | CH ₃ | S | 0 | 64-67 |
| 74 | H | H | COOH | CH ₃ | O | 0 | 188-189 |
| 75 | H | H | CONHC ₆ H ₅ | CH ₃ | O | 0 | 176-178 |
| 76 | H | H | CONHC ₆ H ₅ | CH ₃ | O | 1 | 182-183 |
| 77 | H | H | CONHC ₆ H ₅ | CH ₃ | O | 2 | 193-194 |


- 24 -

TABLE 2A



| CMPD # | R ¹ | R ² | R ³ | R ⁴ | X | n | M.P. (°C) |
|--------|----------------|----------------|----------------|----------------|---|---|-----------|
| 78 | H | H | H | H | S | 2 | 102-104 |
| 79 | H | H | H | H | S | 1 | 106-107 |


TABLE 3



| CMPD # | R ¹ | R ^{''} | X | Y | n | M.P. (°C) |
|--------|----------------|-----------------|---|--------------------------------------|---|-----------|
| 80 | H | H | O | N | 2 | 255 |
| 81 | H | H | O | N | 1 | 190-191 |
| 82 | H | H | O | N | 0 | 143-144 |
| 83 | H | H | S | N | 2 | 226-227 |
| 84 | H | H | S | N | 0 | 150-151 |
| 85 | H | H | S | N | 1 | 192-195 |
| 86 | H | H | S | CH | 0 | 132-134 |
| 87 | H | H | S | CH | 1 | 140-142 |
| 88 | H | H | S | CH | 2 | 150-154 |
| 89 | H | CH ₃ | O | N | 1 | 209-210 |
| 90 | H | CH ₃ | O | N | 2 | 215-216 |
| 91 | H | H | S | C-OCH(CH ₃) ₂ | 1 | oil |

- 25 -

TABLE 4



| CMPD # | R ¹ | R ⁸ | R ⁹ | R ¹⁰ | n | M.P.(°C) |
|--------|----------------|---|----------------------|-----------------|---|----------------------|
| 92 | H | H | F | H | 2 | 136-138 |
| 93 | H | H | F | H | 1 | 132-133 |
| 94 | H | F | F | H | 2 | 106-108 |
| 95 | H | F | F | H | 1 | 128-130 |
| 96 | H | F | F | H | 0 | 63-65 |
| 97 | H | CF ₃ | H | CF ₃ | 1 | 110-113 |
| 98 | H | CF ₃ | H | CF ₃ | 0 | 44-48 |
| 99 | H | CF ₃ | H | CF ₃ | 2 | 76-78 |
| 100 | H | F | H | F | 0 | 103-104 |
| 101 | H | F | H | F | 2 | 108-110 |
| 102 | H | F | H | F | 1 | 138-139 ^a |
| 103 | H | CO ₂ CH(CH ₃) ₂ | Cl | H | 0 | oil |
| 104 | H | CO ₂ CH(CH ₃) ₂ | Cl | H | 1 | 127-129 |
| 105 | H | CO ₂ CH(CH ₃) ₂ | Cl | H | 2 | 82-83 |
| 106 | H | H | CH=NOCH ₃ | H | 1 | 85-87 |
| 107 | H | H | CH=NOCH ₃ | H | 2 | 104-106 |

-26-

Examples of Biological ActivityExample 10Wood Preservative Efficacy Against Bacteria and Yeasts

5 Compositions were prepared by dissolving the
compounds shown in Table 1 in 50% ethanol and further
diluting with sterile distilled water. These dilutions
were pipetted into Petri dishes and mixed with warm
tryptose agar to reach an active ingredient concentration
10 of 10 and 100 ppm. After cooling, the medium was
inoculated with the bacteria listed below. After
sufficient growth of the untreated cultures, the
compounds were evaluated using the following rating
system:

15 0 = growth equal to control
 1 = inhibition of growth by the compound
 2 = no growth under the influence of the compound.
The scores measured for wood preservation efficacy of the
compounds of this invention are listed in Table 5. In
20 this Table, the higher numbers are the most preferred
species.

Causal agents: Bacteria/Yeasts

 Debaryomyces hansenii (yeast)
 Pseudomonas alcaligenes (gram neg)
25 Bacillus cereus mycoides (gram pos)
 Pseudomonas aeruginosa (gram neg)
 Flavobacterium sp. (gram neg)
 Streptomyces albus (gram pos)

-27-

Enterobacter aerogenes (gram neg)

Escherichia coli (gram pos)

- 28 -

TABLE 5

DETAILED SCORES OF THE BACTERICIDAL ACTIVITY OF THE TEST COMPOUNDS

| | P.alcal- genes | | B.cereus mycoides | | P.aeru- ginosa | | D.han- senii | | Flavo- bacter | | S. albus | | E.aero- genes | | E. Coli | |
|-------------|-------------------|--|----------------------|----|-------------------|--|-----------------|----|------------------|----|-------------|----|------------------|----|------------|----|
| Conc. (ppm) | 100 | | 100 | 10 | 100 | | 100 | 10 | 100 | 10 | 100 | 10 | 100 | 10 | 100 | 10 |
| Aq. Dist. | 0 | | 0 | 0 | 0 | | 0 | 0 | 0 | . | 0 | . | 0 | . | 0 | . |
| EtOH | 0 | | 0 | 0 | 0 | | 0 | 0 | 0 | . | 0 | . | 0 | . | 0 | . |
| CMPD # | | | | | | | | | | | | | | | | |
| 1 | 1 | | 2 | 2 | 0 | | 2 | 2 | 2 | . | 2 | . | 0 | . | 2 | . |
| 2 | 0 | | 2 | 0 | 0 | | 2 | 2 | 2 | . | 0 | . | 0 | . | 0 | . |
| 3 | 2 | | 2 | 2 | 1 | | 2 | 1 | 2 | . | 2 | . | 1 | . | 2 | . |
| 4 | 1 | | 2 | 2 | 0 | | 2 | 2 | 2 | . | 2 | . | 0 | . | 2 | . |
| 5 | 0 | | 2 | 0 | 0 | | 2 | 0 | 2 | . | 2 | . | 0 | . | 1 | . |
| 6 | 1 | | 2 | 0 | 0 | | 2 | 2 | 2 | . | 2 | . | 0 | . | 2 | . |
| 7 | 1 | | 2 | 0 | 0 | | 2 | 0 | 2 | . | 0 | . | 0 | . | 0 | . |
| 8 | 2 | | 2 | 0 | 1 | | 2 | 2 | 2 | . | 2 | . | 2 | . | 2 | . |
| 9 | 0 | | 0 | 0 | 0 | | 0 | 0 | 0 | . | 0 | . | 0 | . | 0 | . |
| 10 | 1 | | 2 | 0 | 1 | | 2 | 2 | 2 | . | 2 | . | 0 | . | 2 | . |
| 11 | 1 | | 1 | 0 | 1 | | 2 | 0 | 2 | . | 1 | . | 0 | . | 0 | . |
| 12 | 0 | | 0 | 0 | 0 | | 0 | 0 | 0 | . | 0 | . | 0 | . | 0 | . |
| 13 | 0 | | 2 | 2 | 0 | | 2 | 2 | 2 | . | 2 | . | 0 | . | 2 | . |
| 14 | 1 | | 2 | 2 | 1 | | 2 | 0 | 2 | . | 2 | . | 0 | . | 2 | . |
| 15 | 0 | | 1 | 0 | 0 | | 1 | 0 | 0 | . | 0 | . | 0 | . | 0 | . |
| 16 | 0 | | 2 | 0 | 0 | | 2 | 0 | 0 | . | 0 | . | 0 | . | 0 | . |
| 17 | 0 | | 0 | 0 | 0 | | . | . | 0 | 0 | 0 | 0 | 0 | 0 | 0 | 0 |
| 18 | 1 | | 2 | 0 | 0 | | . | . | 2 | 0 | 2 | 0 | 0 | 0 | 0 | 0 |
| 19 | 0 | | 2 | 0 | 0 | | . | . | 2 | 0 | 2 | 0 | 0 | 0 | 0 | 0 |
| 20 | 0 | | 0 | 0 | 0 | | . | . | 0 | 0 | 0 | 0 | 0 | 0 | 0 | 0 |
| 21 | 2 | | 2 | 2 | 0 | | . | . | 2 | 2 | 2 | 2 | 0 | 0 | 0 | 0 |
| 22 | 1 | | 2 | 2 | 0 | | . | . | 2 | 1 | 2 | 1 | 0 | 0 | 0 | 0 |
| 23 | 0 | | 0 | 0 | 0 | | . | . | 0 | 0 | 0 | 0 | 0 | 0 | 0 | 0 |
| 24 | 0 | | 2 | 2 | 0 | | . | . | 2 | 0 | 2 | 1 | 2 | 0 | 0 | 0 |
| 25 | 1 | | 2 | 2 | 0 | | . | . | 2 | 1 | 2 | 2 | 0 | 0 | 0 | 0 |
| 26 | 0 | | 2 | 2 | 0 | | . | . | 2 | 0 | 2 | 0 | 0 | 0 | 0 | 0 |
| 27 | 1 | | 2 | 2 | 0 | | . | . | 2 | 2 | 2 | 2 | 0 | 0 | 2 | 1 |
| 28 | 0 | | 2 | 1 | 0 | | . | . | 2 | 0 | 2 | 1 | 0 | 0 | 0 | 0 |

Notes for Table 5 Ratings:

0 = growth equal to control

1 = inhibition of growth by the compound

2 = no growth under influence of the compound

-29-

Example 11Wood Preservative Efficacy Against Fungi

The compounds shown in Table 1 were dissolved in 50% ethanol and then diluted with sterile water to give the required concentrations of 1 and 10 ppm in the test agar plates. Malt extract sugar (3%) was added aseptically and uniform distribution was obtained by shaking. Each plate was inoculated with a spore suspension or with a small piece of agar (1 mm) from the margin of an actively growing colony of the test fungus. The fungi employed are listed below. After incubation at 22°C and 70% relative humidity during a period long enough to allow significant growth of untreated controls, the diameters of the fungus colonies were measured and scored using the following rating system:

- 0 = free of fungal growth
- 1 = 25% of fungal growth compared to untreated
- 2 = 50% of fungal growth compared to untreated
- 3 = 75% of fungal growth compared to untreated
- 4 = Growth equal to that of untreated

The scores measured for wood preservation efficacy of the compounds of this invention are listed in Tables 6a and 6b. In these Tables, the lower numbers are the most preferred species.

Causal agents: Fungi

Coriolus versicolor

Coniophora puteana (syn. *C. cerebella*)

Chaetomium globosum

-30-

Aureobasidium pullulans

Penicillium islandicum

Cladosporium resinae (syn Hormonocanis resinae,

Amorphotheca resinae)

5

Aspergillus niger

Aspergillus flavus

Trichoderma viride

Mucor sp.

-31-

TABLE 6A

DETAILED SCORES OF FUNGICIDAL ACTIVITY OF TEST COMPOUNDS

(Test Dosage: 10 ppm)

| <u>CMPD #</u> | <u>C. VER.</u> <u>SICLOR</u> | <u>C.</u> <u>PUTEANA</u> | <u>C. GLO.</u> <u>BOSUM</u> | <u>MUCOR</u> <u>SP</u> | <u>A. PUL.</u> <u>LULANS</u> | <u>P. ISLAN.</u> <u>DICUM</u> | <u>CL</u> <u>RESINAE</u> | <u>A. NIGER</u> | <u>A.</u> <u>FLAVUS</u> | <u>T. VIRIDE</u> |
|---------------|---------------------------------|-----------------------------|--------------------------------|---------------------------|---------------------------------|----------------------------------|-----------------------------|-----------------|----------------------------|------------------|
| CNTRL | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 |
| 1 | 0 | 2 | 0 | - | 3 | 0 | 2 | 0 | 0 | 2 |
| 2 | 2 | 4 | 4 | - | 4 | 4 | 3 | 4 | 4 | 2 |
| 3 | 0 | 2 | 3 | - | 3 | 3 | 4 | 3 | 2 | 3 |
| 4 | 0 | 0 | 0 | - | 2 | 0 | 0 | 0 | 0 | 1 |
| 5 | 3 | 4 | 4 | - | 4 | 4 | 4 | 4 | 4 | 4 |
| 6 | 1 | 0 | 4 | - | 3 | 3 | 4 | 3 | 2 | 4 |
| 7 | 3 | 4 | 4 | - | 4 | 4 | 4 | 4 | 4 | 4 |
| 8 | 0 | 2 | 2 | - | 2 | 0 | 2 | 1 | 1 | 2 |
| 9 | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 |
| 10 | 1 | 3 | 4 | 0 | 4 | 3 | 4 | 4 | 2 | 3 |
| 11 | 0 | 0 | 4 | 0 | 4 | 0 | 4 | 0 | 1 | 2 |
| 12 | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 |
| 13 | 0 | 1 | 0 | 0 | 2 | 2 | 3 | 1 | 2 | 3 |
| 14 | 2 | 3 | 4 | 1 | 4 | 4 | 0 | 3 | 2 | 3 |
| | 0 | 4 | 4 | 4 | 4 | 0 | 4 | 3 | 3 | 4 |
| 16 | 0 | 4 | 4 | 4 | 0 | 0 | 4 | 2 | 4 | 0 |

NOTES:

Rating Scale for Table 6A

- 0 = free of fungal growth
- 1 = 25% of growth compared to untreated control
- 2 = 50% of growth compared to untreated control
- 3 = 75% of growth compared to untreated control
- 4 = growth equal to that of untreated control

- 32 -

TABLE 6B

DETAILED SCORES OF THE FUNGICIDAL ACTIVITY OF THE TEST COMPOUNDS

| CONC (ppm) | <u>G. VER-</u> <u>SICLOR</u> | | <u>G.</u> <u>PUTEANA</u> | | <u>C. GLO-</u> <u>BOSUM</u> | | <u>MUCOR SP</u> | | <u>A. PUL-</u> <u>LULANS</u> | <u>P. ISLAN-</u> <u>DICUM</u> | <u>CL</u> <u>RESINAE</u> | <u>A. NIGER</u> | <u>A. FLAVUS</u> | | <u>T. VIRIDE</u> |
|---------------|---------------------------------|---|-----------------------------|---|--------------------------------|-----|-----------------|----|---------------------------------|----------------------------------|-----------------------------|-----------------|------------------|---|------------------|
| | 10 | 1 | 10 | 1 | 10 | 100 | 10 | 10 | 10 | 10 | 10 | 10 | 10 | 1 | 10 |
| Aq. Dist. | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 |
| EtOH | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 | 4 |
| <u>CMPD #</u> | | | | | | | | | | | | | | | |
| 17 | 4 | | 4 | | 4 | 4 | | | | | | | 4 | | |
| 18 | 0 | 1 | 0 | | 0 | 0 | | 4 | 0 | 1 | 0 | 0 | 0 | 3 | 2 |
| 19 | 0 | 2 | 3 | | 0 | 2 | | 3 | 0 | 0 | 0 | 0 | 0 | | 2 |
| 20 | 4 | | 4 | | 4 | 4 | | 4 | 4 | 4 | 4 | 4 | 4 | | 4 |
| 21 | 0 | 3 | 0 | | 2 | 0 | 1 | 2 | 0 | 0 | 0 | 0 | 0 | 3 | 4 |
| 22 | 2 | | 0 | 3 | 4 | 0 | | 4 | 2 | 4 | 3 | 2 | | | 3 |
| 23 | 4 | | 4 | | 4 | 4 | | 4 | 4 | 4 | 4 | 4 | 4 | | 4 |
| 24 | 0 | | 3 | | 4 | 4 | | 4 | 0 | 0 | 0 | 0 | 0 | | 2 |
| 25 | 0 | 3 | 0 | 2 | 3 | 0 | 3 | 3 | 1 | 0 | 0 | 0 | 0 | | 2 |
| 26 | 4 | | 4 | | 4 | 2 | | 4 | 4 | 4 | 4 | 4 | 4 | | 3 |
| 27 | 0 | | 0 | 3 | 4 | 0 | | 4 | 4 | 0 | 3 | 3 | | | 2 |
| 28 | 3 | | 0 | | 4 | 1 | | 4 | 4 | 4 | 4 | 4 | 3 | | 3 |

NOTES:

Rating Scale for Table 6B

- 0 = free of fungal growth
- 1 = 25% of growth compared to untreated control
- 2 = 50% of growth compared to untreated control
- 3 = 75% of growth compared to untreated control
- 4 = growth equal to that of untreated control

-33-

Example 12Control of Molds and Blue Stain Fungi in Stick Test

The compounds shown in Table 1 were dissolved in 50% ethanol and a dilution series was made using the same solvent. In 25 ml of each dilution, one oven-dried beech stick (73 x 18 x 2 mm) was drenched until saturated.

Test dosages were 50, 100, 250, 500, and 1000 ppm for blue stain fungi which were *Aureobasidium pullulans* and *Sclerophoma pithyophila*. Test dosages for the molds used (*Trichoderma viride*, *Aspergillus niger*) were 250, 500, 1000, 2500, and 5000 ppm.

After three hours the test solution was poured off and each stick was allowed to dry in a sterile laminar air flow. In each Petri dish one stick was placed on malt agar previously seeded with inoculum. Two drops of fungal or spore suspension were pipetted on the upper surface of the stick. The Petri dishes were then incubated at 22°C and 90% relative humidity. The treated sticks were evaluated after sufficient growth of the fungus on the untreated control sticks. The following score system was used to rate the effectiveness of the compounds:

- 0 = stick free of fungal growth
- 1 = traces of fungal growth on stick
- 2 = slight fungal growth (5 to 25% of the surface covered)
- 3 = moderate fungal growth (25 to 50% of the surface covered)

-34-

4 = vigorous fungal growth (greater than 50% of the surface covered).

5 For purposes of comparison of these compounds, these values were converted to threshold ranges. The threshold value in this system is defined as the minimum concentration of a particular compound which produces a score less than or equal to 1. These values are presented in Table 7.

- 35 -

TABLE 7THRESHOLD VALUES (PPM) OF TEST COMPOUNDS IN STICK TEST

| <u>COMPOUND #</u> | <u>FUNGI</u> | | | |
|-------------------|------------------------------------|------------------------------------|--------------------------|---------------------------|
| | <u>AUREOBASIDIUM PULLULANS</u> | <u>SCLEROPHOMA PYTHIOPHILA</u> | <u>ASPERGILLUS NIGER</u> | <u>TRICHODERMA VIRIDE</u> |
| 1 | > 1000 | 100-250 | 1000-2500 | 2500-5000 |
| 4 | 500-1000 | 50-100 | 250-500 | 500-1000 |
| 8 | 250-500 | 50-100 | 250-500 | 500-1000 |
| 11 | 1000 | < 50 | 500-1000 | 2500-5000 |
| 13 | 500-1000 | 250-500 | 500-1000 | 1000-2500 |
| 16 | > 1000 | 100-250 | > 5000 | > 5000 |
| 18 | 500-1000 | 100-250 | 250-500 | < 250 |
| 19 | 250-500 | 250-500 | 250-500 | < 250 |
| 21 | 250-500 | 50-100 | < 250 | < 250 |
| 24 | 500-1000 | 250-500 | 250-500 | 500-1000 |
| 25 | 250-500 | 50-100 | < 250 | < 250 |
| 27 | > 1000 | 500-1000 | 500-1000 | < 250 |

-36-

Example 13Activity Against Wood-Rotting Fungi such as *Coriolus versicolor* and *Coniophora puteana*

5 Sapwood blocks (50 x 20 x 6 mm) of Scots pine (*Pinus sylvestris*) and beech (*Fagus sylvatica*) were oven-dried at 104°C. The blocks were cooled, weighed, and impregnated with the test compound, by a vacuum treatment. Each concentration of the test compounds was applied to 7 replicates. By reweighing after each treatment, the uptake of active ingredient was calculated. Badly treated wood was discarded. For fixation of the active compound, the treated blocks were kept in a closed container for two weeks. The container was opened and the wood was dried for two more weeks. The test blocks were sterilized by gamma-irradiation (1.2 Mrad). Each treated block was placed on a mesh in an inoculated Petri dishes of malt agar, with an untreated (control) block.

10

15

20 All the blocks were exposed to fungal attack for eight weeks at 22°C and 70% relative humidity. At the end of the incubation period, the blocks were freed from adhering mycelium, oven dried at 104°C, allowed to cool, and weighed. The percentage weight loss of each block was calculated. Invalid results, due to waterlogging or insufficient moisture content, were not taken into account.

25

The average weight loss of the treated blocks compared to the control blocks appears in Table 8.

- 37 -

TABLE 8

AVERAGE WEIGHT LOSS OF BLOCKS TREATED WITH TEST COMPOUNDS

| CMPD # | UPTAKE g.a.i./m3 | <u>CORIOLUS</u> | | UPTAKE g.a.i./m3 | <u>CONIOPHORA</u> | |
|--------|---------------------|--------------------------|--------------------------|---------------------|--------------------------|--------------------------|
| | | % WEIGHT LOSS TREATED | % WEIGHT LOSS CONTROL | | % WEIGHT LOSS TREATED | % WEIGHT LOSS CONTROL |
| 4 | 477 | 35 | 32 | 568 | 0.3 | 17 |
| | 1205 | 35 | 41 | 1356 | 0.3 | 21 |
| 6 | 482 | 25 | 33 | 555 | 0.0 | 29 |
| | 1163 | 19 | 41 | 1373 | -0.1 | 20 |
| 8 | 494 | 24 | 34 | 536 | 0.9 | 25 |
| | 1184 | 3.5 | 26 | 1346 | 0.7 | 31 |
| 11 | 485 | 5.4 | 29 | 530 | ND | ND |
| | 1162 | 8.3 | 30 | 1346 | 1.8 | 28 |
| 13 | 492 | 27 | 31 | 530 | -0.2 | 34 |
| | 1202 | 9.0 | 31 | 1271 | 0.1 | 32 |
| 18 | 488 | 32 | 31 | 579 | 0.0 | 41 |
| | 1173 | 39 | 40 | 1534 | -0.3 | 35 |
| 19 | 472 | 35 | 29 | 573 | 0.9 | 42 |
| | 1222 | 87 | 35 | 1456 | -0.3 | 37 |
| 21 | 496 | 38 | 35 | 582 | -0.1 | 42 |
| | 1203 | 22 | 33 | 1456 | -0.5 | 35 |
| 24 | 450 | 39 | 37 | 545 | 17.3 | 30 |
| | 1136 | 35 | 39 | 1374 | 0.9 | 29 |
| 25 | 482 | 37 | 38 | 533 | -0.7 | 30 |
| | 1175 | 21 | 44 | 1358 | -0.8 | 33 |
| 27 | 479 | 32 | 31 | 526 | 0.7 | 36 |
| | 1203 | 36 | 37 | 1347 | -0.5 | 34 |

NOTES FOR TABLE 8:

ND = NO DATA

-38-

Example 14In Vitro Activity Against Molds and Blue-Stain Fungi

Representative compounds were dissolved (2000 ppm) in a 2:3 solution of acetone:ethanol. The effect of the representative compounds on the growth of certain molds and blue-strain fungi were determined using a poison plate assay according to the following procedure: The solutions of the representative compounds prepared above were further diluted with sterile water to desired concentrations and poured into Petri dishes. Malt extract agar medium was then added aseptically to the Petri dishes and to Petri dishes containing no compound (controls). The Petri dishes were then shaken to provide a uniform distribution of the agar medium. Each Petri dish containing compound and each control Petri dish, was then inoculated with a fungus and incubated for a period of time sufficient to permit complete growth of the fungus in the respective control Petri dish. The Petri dishes containing compound were then examined to determine the amount of inhibition of fungi for each concentration of compound tested. The lowest concentration of compound which resulted in complete inhibition of a particular fungus was determined and recorded in Tables 9A and 9B below as the minimum inhibitory concentration (MIC) values.

- 39 -

TABLE 9A

MIC (ppm) of Compounds against Fungi

| <u>Compound #</u> | <u>8</u> | <u>34</u> | <u>57</u> | <u>58</u> | <u>60</u> | <u>61</u> | <u>83</u> | <u>85</u> | <u>87</u> |
|--------------------|----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|
| A. amstelodami | 10 | 5 | 10 | 5 | 5 | 5 | >25 | 5 | 5 |
| A. niger | 25 | 5 | 10 | 5 | 5 | <1 | >25 | 5 | 2.5 |
| A. versicolor | 10 | 5 | 10 | 5 | 2.5 | 2.5 | 25 | 2.5 | 2.5 |
| A. pullulans | >25 | 25 | >25 | 25 | 25 | 10 | >25 | 25 | 10 |
| C. cladosporioides | >25 | 25 | 25 | 10 | 25 | 10 | >25 | 25 | 25 |
| C. pilifera | 5 | 2.5 | 10 | 5 | 5 | 2.5 | 10 | 2.5 | 2.5 |
| F. solani | 25 | 25 | 25 | 10 | 10 | 5 | >25 | 25 | 10 |
| G. candidum | >25 | 25 | 25 | 25 | 25 | 10 | >25 | 10 | 25 |
| P. purpurogenum | >25 | 10 | 10 | 10 | 25 | 5 | >25 | 10 | 2.5 |
| P. variotii | >25 | 25 | 25 | 25 | 10 | 5 | >25 | 25 | 10 |
| P. violacea | 25 | 25 | 25 | 25 | 10 | 25 | >25 | 10 | 10 |
| S. atra | 10 | 5 | 10 | 5 | 5 | 2.5 | 5 | 2.5 | 2.5 |
| S. entoxylina | 10 | 5 | 10 | 5 | 5 | 10 | 10 | 5 | 5 |
| T. viride | >25 | >25 | >25 | 25 | 25 | 10 | >25 | 25 | 10 |
| U. atrum | 25 | 25 | 25 | 10 | 10 | 10 | >25 | 10 | 10 |

- 40 -

TABLE 9BMIC (ppm) of Compounds against Fungi

| <u>Compound #</u> | <u>A</u> | <u>4</u> | <u>19</u> | <u>21</u> |
|--------------------|----------|----------|-----------|-----------|
| A. amstelodami | 25 | 10 | 25 | 10 |
| A. niger | 5 | 2.5 | 2.5 | 5 |
| A. versicolor | 10 | 5 | 25 | 2.5 |
| A. ;ullulans | 10 | 10 | 25 | 25 |
| C. cladosporioides | 25 | 10 | 25 | 25 |
| C. pilifera | 10 | 5 | 10 | 2.5 |
| F. solani | > 25 | 10 | > 25 | 10 |
| G. candidum | > 25 | 25 | > 25 | 25 |
| P. purpurogenum | 10 | 10 | 25 | 10 |
| P. variotii | 25 | 10 | 25 | 10 |
| P. violacea | > 25 | 25 | > 25 | 10 |
| S. atra | 10 | 2.5 | 25 | 2.5 |
| S. entoxylina | 25 | 10 | 25 | 10 |
| T. viride | 25 | 25 | 25 | 25 |
| U. atrium | > 25 | 25 | > 25 | 10 |

A = 3,4-dichlorophenyl-1,4,2-oxathiazone

Example 15Activity against Blue-Stain Fungi and Molds on a Stick
Test on Vermiculite

5 Beech sticks (73x18x2 mm) *Fagus sylvatica* were painted, allowed to dry, and sterilized by γ -radiation (1.2 mRad). Sticks were treated by coating each stick with a film containing 0.15% or 0.3% of the tested compound in a water-based placebo paint.

10 The coated sticks prepared above were then dipped in a spore suspension of pure culture of each fungus. Seven sticks each were placed in autoclaved Petri dishes (200 mm in diameter, 30 mm in height) containing 300 ml of vermiculite and 120 ml of water, and incubated for 12
15 weeks. The surfaces of the sticks were then examined for the growth of fungus and were evaluated according to the following scoring system:

0: No growth

1: Trace of growth of up to 1% coverage of the test
20 inoculated area

2: Growth covering between 1 and 10% of the inoculated test area

3: Growth covering between 10 and 30% of the inoculated test area

25 4. Growth covering between 30 and 70% of the inoculated test area

5. Growth covering more than 70% of the inoculated test area.

The scores of compounds tested are presented in Table 10.

- 42 -

TABLE 10

Surface Scores of Wooden Sticks
Treated with Paint Formulation

| <u>Organisms</u> | <u>Compounds/% a. i.</u> | | | | | | | | | | | | | | |
|--------------------|--------------------------|------------|-------------|------------|-------------|------------|-------------|------------|-------------|------------|-------------|------------|-------------|------------|----------------|
| | <u>8</u> | | <u>34</u> | | <u>36</u> | | <u>37</u> | | <u>38</u> | | <u>41</u> | | <u>42</u> | | <u>Control</u> |
| | <u>0.15</u> | <u>0.3</u> | <u>0.15</u> | <u>0.3</u> | <u>0.15</u> | <u>0.3</u> | <u>0.15</u> | <u>0.3</u> | <u>0.15</u> | <u>0.3</u> | <u>0.15</u> | <u>0.3</u> | <u>0.15</u> | <u>0.3</u> | |
| A. versicolor | 0 | 0 | 0 | 0 | 0 | 0 | 2 | 1 | 1 | 0 | 0 | 0 | 2 | 1 | 5 |
| A. pullulans | 0 | 0 | 0 | 0 | 0 | 0 | 3 | 2 | 2 | 0 | 0 | 0 | 2 | 1 | 5 |
| C. cladosporioides | 0 | 0 | 0 | 0 | 0 | 0 | 3 | 0 | 2 | 0 | 0 | 0 | 2 | 1 | 5 |
| P. purpurogenum | 0 | 0 | 4 | 1 | 1 | 1 | 3 | 1 | 3 | 3 | 2 | 1 | 4 | 2 | 5 |
| P. violacea | 4 | 0 | 4 | 1 | 3 | 1 | 5 | 4 | 4 | 4 | 4 | 3 | 4 | 3 | 5 |
| R. rubra (y) | 1 | 1 | 3 | 0 | 0 | 0 | 4 | 3 | 3 | 0 | 3 | 0 | 3 | 1 | 5 |
| S. chartarum | 0 | 0 | 1 | 0 | 0 | 0 | 1 | 0 | 5 | 2 | 4 | 0 | 3 | 2 | 5 |
| U. atrum | 1 | 1 | 3 | 1 | 3 | 1 | 4 | 3 | 4 | 3 | 3 | 1 | 5 | 3 | 5 |

y = yeast

0 = No growth

1 = Trace of growth of up to 1% coverage of the test inoculated area.

2 = Growth more than 1% and up to 10% coverage of test inoculated area.

3 = Growth more than 10% and up to 30% coverage of test inoculated area.

4 = Growth more than 30% and up to 70% coverage of test inoculated area.

5 = Growth more than 70% coverage of test inoculated area.

-43-

Example 16Activity against Blue-Stain Fungi and Molds in a Stick Test

5 Representative compounds of this invention were dissolved in 50% ethanol. Each compound was then diluted serially using 50% ethanol. Four (4) oven-dried beech sticks (73 x 18 x 2 mm) were drenched until saturated in 25ml of each dilution of each compound, to prepare the
10 treated sticks. After three (3) hours, the solutions containing the test compounds were poured off and the treated sticks were allowed to dry in a sterile laminar air flow. Each treated stick was then placed in a Petri dish which had been previously seeded with inoculum. Two
15 drops of a test fungal or spore suspension were pipetted onto the upper surface of each treated stick. The Petri dishes containing the treated sticks were incubated at 22°C and 90% relative humidity. The treated sticks were evaluated after there was sufficient growth of fungus on
20 control sticks (i.e., untreated sticks) incubated in the same manner. The following score system was used:

- 0: Stick free of fungal/mold growth
- 1: Traces of fungal growth on the stick
- 2: Slight growth (5 to 25% of the surface covered
25 with fungal growth)
- 3: Moderate growth (25 to 50% covered with fungal growth)
- 4. Vigorous to maximum fungal growth (more than 50% growth)

-44-

The threshold (minimum) concentration of each compound tested necessary to obtain a score of 1-2 or 0, for each fungus tested is presented in Table 11 below.

- 45 -

TABLE 11

Threshold Concentrations (ppm) against Blue-stain Fungi and Molds in a Stick Test

| CMPD # | Fungi/Mold | | | | | | | |
|--------|---------------|---------|-------------|---------|-----------|---------|-------------|---------|
| | Aureobasidium | | Sclerophoma | | A. niger | | Trichoderma | |
| | score 1-2 | score 0 | score 1-2 | score 0 | score 1-2 | score 0 | score 1-2 | score 0 |
| 8 | 250-500 | > 1000 | 50-100 | 100 | 250-500 | 1000 | 500-1000 | 1000 |
| 34 | 250-500 | > 1000 | < 50 | 100 | < 250 | 500 | 500-1000 | 2500 |
| 50 | 100-500 | > 1000 | 50-100 | 100 | 250-500 | 1000 | 1000-2500 | 5000 |
| 51 | 250-500 | > 1000 | 50-100 | 100 | 250-500 | 500 | 500-1000 | 1000 |
| 54 | 250-500 | 500 | < 50 | 100 | < 250 | 500 | 500-1000 | 5000 |
| 57 | 250-500 | > 1000 | < 50 | 100 | < 250 | 500 | 500-1000 | 1000 |
| 58 | 500-1000 | > 1000 | < 50 | 100 | < 250 | 500 | 1000-2500 | 5000 |
| 60 | 100-250 | 1000 | < 50 | 100 | < 250 | 500 | 500-1000 | 2500 |
| 61 | 250-500 | > 1000 | < 50 | 100 | < 250 | < 250 | 1000-2500 | 2500 |
| 81 | 250-500 | > 1000 | < 50 | 250 | 250-500 | 500 | 500-1000 | 2500 |
| 85 | 250-500 | 1000 | < 50 | 100 | < 250 | 1000 | 1000-2500 | 2500 |
| 87 | 100-250 | 1000 | 50-100 | 100 | 250-500 | 1000 | 1000-2500 | 5000 |
| 89 | 100-250 | > 1000 | < 50 | 250 | 250-500 | 500 | 1000-2500 | 2500 |

0: Stick free of fungal growth

1: Traces of fungal growth on the stick

2: Slight growth (5 to 25% of the surface covered with fungal growth)

-46-

Example 17Activity against Blue-Stain Fungi and Molds in a Mold Cabinet Test

5 Using the methods described in BS3900: Part G6:
1989, British Standard Methods of test for paints,
"Assessment of resistance to fungal growth",
representative compounds of this invention were tested
for activity against blue-stain fungus and molds in a
10 mold cabinet test.

In brief, sticks of Scots pine (*Pinus sylvestris*)
measuring 75 x 100 x 10 mm, were painted, allowed to dry,
and sterilized by γ -radiation (1.2 mRad).

Solutions of the tested compounds (0.15% and 0.3%)
15 in water-based placebo paint were prepared. The sticks
were then with each solution. The inoculation consisted
of dipping the sticks in a mixed spore suspension, then
placing them in a mold chamber and incubating them for 12
weeks. The surfaces were evaluated according the
20 following score system:

0: No growth

1: Trace of growth of up to 1% coverage of the
inoculated test area

2: Growth covering between 1 and 10% of the
25 inoculated test area

3: Growth covering between 10 and 30% of the
inoculated test area

4. Growth covering between 30 and 70% of the
inoculated test area

-47-

5. Growth covering more than 70% of the inoculated test area.

The scores of compounds tested are presented in Table 12.

- 48 -

TABLE 12**Surface Scores in a Paint Formulation in a Mold Cabinet Test**

| <u>Compound #</u> | <u>Concentration (%)</u> | <u>Surface Score</u> | |
|-------------------|--------------------------|----------------------|-----------------|
| | | <u>6 weeks</u> | <u>12 weeks</u> |
| 8 | 0.15 | 0 | 2.0 |
| | 0.3 | 0 | 1.5 |
| 34 | 0.15 | 0.5 | 1.5 |
| | 0.3 | 0 | 1.0 |
| 36 | 0.15 | 2.5 | 4.5 |
| | 0.3 | 2.5 | 4.0 |
| 37 | 0.15 | 4.0 | 5.0 |
| | 0.3 | 0 | 0 |
| 38 | 0.15 | 2.5 | 4.5 |
| | 0.3 | 2.5 | 4.0 |
| 41 | 0.15 | 0 | 2.0 |
| | 0.3 | 0.5 | 3.0 |
| 42 | 0.15 | 1.5 | 3.5 |
| | 0.3 | 0.5 | 3.0 |
| Placebo | . | 5.0 | 5.0 |

0 = No growth

1 = Trace of growth of up to 1% coverage of the test inoculated area.

2 = Growth more than 1% and up to 10% coverage of test inoculated area.

3 = Growth more than 10% and up to 30% coverage of test inoculated area.

4 = Growth more than 30% and up to 70% coverage of test inoculated area.

5 = Growth more than 70% coverage of test inoculated area.

-49-

Example 18Control of Molds and Sapstain Fungi in Mini-Board Test

Representative compounds of this invention to be
5 tested, were suspended in an aqueous solution containing
7.5% GENAPOL X 080™ (Hoechst-Celanese Corporation), and
20% propylene glycol monomethyl ether, to prepare the
test solutions. The concentration of the test compound
in the test solution was 5000 ppm.

10 Deep frozen boards (300 x 50 x 10 mm) of freshly
felled sapwood of *Pinus sylvestrus* (mini-boards) were
thawed at room temperature. One half of each mini-board
was immersed in a test solution for 20 seconds. The
mini-boards were then sprayed with mixed spore suspension
15 containing the following fungi:

Aureobasidium pullulans,
Aspergillus amstelodami,
Ceratocystis pilifera,
Cladosporium sp.,
20 Penicillium sp.,
Sclerophomas entoxylina, and
Trichoderma viride,

and stored in incubation boxes at 25°C and at 100%
relative humidity, for three weeks. For each compound
25 tested, each concentration of test solution was applied
to five different mini-boards.

The efficacy of the test compounds was determined by
comparing the fungal growth on both the treated and
untreated parts of the mini-boards.

-50-

The degree of infection was scored according to the following scale:

- 0 = Free of fungal growth
- 1 = Traces of fungal growth
- 5 2 = Little fungal growth
- 3 = Moderate fungal growth
- 4 = Vigorous to maximum growth (all surfaces covered with fungal growth)

The results of the mini-board evaluation are
10 presented in Table 13 below.

- 51 -

TABLE 13**Surface Scores of Treated Mini-Boards**

| <u>CMPD #</u> | <u>3 Week Incubation</u> | | <u>6 Week Incubation</u> | |
|----------------------|---------------------------------|------------------------|---------------------------------|------------------------|
| | <u>1500 ppm</u> | <u>2500 ppm</u> | <u>1500 ppm</u> | <u>2500 ppm</u> |
| 8 | 0 | 0 | 0.8 | 0.4 |
| 34 | 0 | 0 | 2.4 | 2.4 |
| 36 | 0.2 | 0 | 2.6 | 1.4 |
| 37 | 0 | 0 | 0.8 | 0.4 |
| 38 | 0.6 | 0.4 | 2.0 | 2.8 |
| 41 | 0.6 | 0.2 | 2.4 | 1.6 |
| 42 | 0 | 0 | 2.0 | 2.6 |
| 48 | 0 | 0 | 1.4 | 0.8 |
| 49 | 0 | 0 | 1.8 | 1.2 |
| 78 | 0.2 | 0.2 | 1.2 | 1.8 |
| 79 | 1.0 | 0 | 3.0 | 1.8 |

0 = Free of fungal growth

1 = Traces of fungal growth

2 = Little fungal growth


3 = Moderate fungal growth

4 = Vigorous to maximum growth (all surfaces covered with fungal growth)

-52-


What is claimed is:

1. A compound of the formula




- 10 wherein n is 0, 1 or 2; R₁ is hydrogen, C₁-C₄ linear or branched alkyl, or benzyl; and Q is:

(a)



- wherein R², R³ and R⁴ are, individually, hydrogen, alkyl, alkoxy, alkylthio, alkoxycarbonyl, halogen, trihalomethyl, cyano, acetyl, formyl, benzoyl, nitro, alkoxyaminomethyl, phenyl or phenylaminocarbonyl, wherein the alkyl or alkoxy moieties are all C₁-C₄, linear or branched, with the proviso that at least one of R², R³ or R⁴ must be other than hydrogen;

(b)




- wherein R⁵, R⁶ and R⁷ are, individually, hydrogen, C₁-C₄ alkoxy, C₁-C₄ alkylthio, halogen, trihalomethyl, cyano, acetyl, formyl, benzoyl, nitro, phenyl or

-53-

phenylaminocarbonyl, with the proviso that at least one of R^5 , R^6 or R^7 must be other than hydrogen;

(c)




5

wherein R^8 , R^9 and R^{10} are, individually, hydroxyl, halo, C_1 - C_{12} alkyl, C_5 - C_6 cycloalkyl, trihalomethyl, phenyl, C_1 - C_5 alkoxy, C_1 - C_5 alkylthio, tetrahydropyranyloxy, phenoxy, $(C_1$ - C_4 alkyl)carbonyl, phenylcarbonyl, C_1 - C_4 alkylsulfinyl, C_1 - C_4 alkylsulfonyl, carboxy or its alkali metal salt, $(C_1$ - C_4 alkoxy)carbonyl, $(C_1$ - C_4 alkyl)aminocarbonyl, phenylaminocarbonyl, tolylaminocarbonyl, morpholinocarbonyl, amino, nitro, cyano, dioxolanyl, or $(C_1$ - C_4 alkoxy)iminomethyl; or

10

15

(d)



wherein X is oxygen or sulfur; Y is nitrogen, $-CH-$, or $-C(C_1-C_4 \text{ alkoxy})-$; and R'' is hydrogen or C_1 - C_4 alkyl.

20

2. A compound as recited in claim 1 wherein R^1 is hydrogen or C_1 - C_4 alkyl; n is 1 or 2; R^2 , R^3 and R^4 are, individually, hydrogen, C_1 - C_4 alkyl, halo, $(C_1$ - C_4 alkoxy)-carbonyl, or cyano, with the proviso that at least one of R^2 , R^3 and R^4 must be other than hydrogen; R^5 , R^6 and R^7 are, individually, hydrogen, halo or cyano, with the proviso that at least one of R^5 , R^6 and R^7 must be other than hydrogen; R^8 , R^9 and R^{10} are C_1 - C_4 alkyl, C_1 - C_4


25

-54-

alkoxy, nitro, halo, trihalomethyl, or (C₁-C₄ alkoxy)-carbonyl; X is sulfur; and R" is hydrogen.

3. A compound as recited in claim 2 wherein R¹ is hydrogen; n is 1 or 2; R², R³ and R⁴ are, individually, hydrogen, methyl, ethyl, bromo, chloro, ethyl carboxylate, or cyano, with the proviso that at least one of R², R³ and R⁴ must be other than hydrogen; R⁵, R⁶ and R⁷ are, individually, hydrogen, bromo, chloro or cyano, with the proviso that at least one of R⁵, R⁶ and R⁷ must be other than hydrogen; R⁸, R⁹ and R¹⁰ are methyl, ethyl, nitro, flouro, chloro, or trifluoromethyl.

4. A method for preserving wood or a composite wood material which comprises treating the wood or the composite wood material with a fungicidally or bactericidally effective amount of a compound of the formula



(II)


wherein n is 0, 1 or 2; R¹ is hydrogen, C₁-C₄ linear or branched alkyl, or benzyl; and R is:

(a) phenyl; naphthyl; phenyl substituted with 1-3 of the following substituents:

-55-

hydroxyl, halo, C₁-C₁₂ alkyl, C₅-C₆ cycloalkyl,
 trihalomethyl, phenyl, C₁-C₅ alkoxy, C₁-C₅ alkylthio,
 tetrahydropyranyloxy, phenoxy, (C₁-C₄ alkyl)carbonyl,
 phenylcarbonyl, C₁-C₄ alkylsulfinyl, C₁-C₄
 5 alkylsulfonyl, carboxy or its alkali metal salt,
 (C₁-C₄ alkoxy)carbonyl, (C₁-C₄ alkyl)aminocarbonyl,
 phenylaminocarbonyl, tolylaminocarbonyl,
 morpholinocarbonyl, amino, nitro, cyano, dioxolanyl,
 or (C₁-C₄ alkoxy)iminomethyl;
 10 pyridinyl; thienyl; furanyl; or thienyl or furanyl
 substituted with 1 to 3 of the following groups:
 alkyl, alkoxy, alkylthio, alkoxycarbonyl, halogen,
 trihalomethyl, cyano, acetyl, formyl, benzoyl,
 nitro, phenyl or phenylaminocarbonyl, wherein the
 15 alkyl or alkoxy moiety is C₁-C₄, linear or branched;
 or

(b)



20 wherein X is oxygen or sulfur; Y is nitrogen, -CH-, or
 -C(C₁-C₄ alkoxy)-; and R'' is hydrogen or C₁-C₄ alkyl.

5. A method as recited in claim 4 wherein R¹ is
 hydrogen, n is one or two, and R has one or 2 of the
 25 following values:

phenyl, (C₁-C₆ alkyl)phenyl, halophenyl,
 dihalophenyl, biphenyl, (C₁-C₅ alkyloxy)phenyl,
 trihalomethylphenyl, nitrophenyl, phenyl substituted with

-56-


(C₁-C₄ alkoxy)carbonyl, furanyl, furanyl substituted by ethyl carboxylate, cyano, chlorine, or bromine, thienyl, thienyl substituted with ethyl carboxylate, cyano, chlorine, or bromine, or (C₁-C₆ alkyl)nitrophenyl.

5

6. A method as recited in claim 5 wherein R¹ is hydrogen, n is one or two, and R is represented by:
4-chlorophenyl, 3-nitrophenyl, 3,4-dichlorophenyl,
3-fluorophenyl, 2-thienyl, 4-methylphenyl,
10 3-trifluoromethylphenyl, 3-ethanone phenyl,
3,5-dichlorophenyl, 4-trifluoromethylphenyl, or
3-methyl-4-nitrophenyl.

15

7. A method as recited in claim 4 wherein R¹ is hydrogen, and R is



20

wherein X is sulfur, Y is nitrogen or -CH-, and R'' is hydrogen.

25


8. A method as recited in claim 4 wherein between about 0.05 to 0.4kg/m² of the compound is applied to the surface area of the wood or the composite wood material.

9. A method as recited in claim 4 wherein about 0.5 to about 6.0 kg/m³ of the compound is applied into the wood or the composite wood material.

-57-

10. A composition for preserving wood or a composite wood material which comprises:

a) an effective amount of a compound having the formula



(II)

wherein n is 0, 1 or 2; R¹ is hydrogen, C₁-C₄ linear or branched alkyl, or benzyl; and

R is:

(a) phenyl; naphthyl; phenyl substituted with 1-3 of the following substituents:

hydroxyl, halo, C₁-C₁₂ alkyl, C₅-C₆ cycloalkyl, trihalomethyl, phenyl, C₁-C₅ alkoxy, C₁-C₅ alkylthio, tetrahydropyranyloxy, phenoxy, (C₁-C₄ alkyl)carbonyl, phenylcarbonyl, C₁-C₄ alkylsulfinyl, C₁-C₄ alkylsulfonyl, carboxy or its alkali metal salt, (C₁-C₄ alkoxy)carbonyl, (C₁-C₄ alkyl)aminocarbonyl, phenylaminocarbonyl, tolylaminocarbonyl, morpholinocarbonyl, amino, nitro, cyano, dioxolanyl, or (C₁-C₄ alkoxy)iminomethyl;

pyridinyl; thienyl; furanyl; or thienyl or furanyl substituted with 1 to 3 of the following groups:

alkyl, alkoxy, alkylthio, alkoxycarbonyl, halogen, trihalomethyl, cyano, acetyl, formyl, benzoyl,


-58-

nitro, alkoxyaminomethyl, phenyl or phenylaminocarbonyl, wherein the alkyl or alkoxy moiety is C₁-C₄, linear or branched;

or

5

(b)



wherein X is oxygen or sulfur; Y is nitrogen, -CH-, or -C(C₁-C₄ alkoxy)-; and R' is hydrogen or C₁-C₄ alkyl; and

10

b) a suitable carrier.

11. A composition as recited in claim 8 wherein R¹ is hydrogen, n is one or two, and R is one or 2 of the following:

15

phenyl, (C₁-C₆ alkyl)phenyl, halophenyl, dihalophenyl, biphenyl, (C₁-C₅ alkyloxy)phenyl, trihalomethylphenyl, nitrophenyl, phenyl substituted with (C₁-C₄ alkoxy)carbonyl, furanyl, furanyl substituted by ethyl carboxylate, cyano, chlorine, or bromine, thienyl, thienyl substituted with ethyl carboxylate, cyano, chlorine, or bromine, or (C₁-C₆ alkyl)nitrophenyl.

20

12. A composition as recited in claim 9 wherein R¹ is hydrogen, n is one or two, and R is:

25


4-chlorophenyl, 3-nitrophenyl, 3,4-dichlorophenyl, 3-fluorophenyl, 2-thienyl, 4-methylphenyl, 3-trifluoromethylphenyl, 3-ethanone phenyl, 3,5-dichlorophenyl, 4-trifluoromethylphenyl, or

-59-

3-methyl-4-nitrophenyl.

13. A composition as recited in claim 8 wherein R¹ is hydrogen, and R is

5



wherein X is sulfur, Y is nitrogen or -CH-, and R'' is hydrogen.

10

14. A composition as recited in claim 8 wherein the carrier is a diluent selected from the group consisting of an organic solvent and water.

15

15. A composition as recited in claim 8 wherein the carrier includes at least one of an organic binding agent, a fixative, or a plasticizer.

20

16. A composition as recited in claim 1 wherein the carrier contains at least one of a dye, a pigment, or a stabilizer.

25

17. A composition as recited in claim 12 wherein the solvent includes an organic binding agent or fixative.

18. A composition as recited in claim 8 wherein from about 0.001% by weight up to about 10% by weight of

-60-

the compound based on the total composition is present.

19. A composition as recited in claim 8 wherein
from about 0.1 to 5% by weight of the compound based on
5 the total composition is present.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 94/09702A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C07D291/06 B27K3/34 C07D419/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C07D B27K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

| Category * | Citation of document, with indication, where appropriate, of the relevant passages | Relevant to claim No. |
|------------|---|-----------------------|
| X | EP,A,0 104 940 (UNIROYAL, INC. ET AL.) 4 April 1984 cited in the application see claim 7 | 10-19 |
| A | see the whole document cited in the application --- | 1-9 |
| A | EP,A,0 363 316 (CIBA-GEIGY AG) 11 April 1990 see the whole document ----- | 1-19 |

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

15 November 1994

Date of mailing of the international search report

21. 11. 94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+ 31-70) 340-3016

Authorized officer

Allard, M

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/US 94/09702

| Patent document cited in search report | Publication date | Patent family member(s) | Publication date |
|---|---------------------|----------------------------|---------------------|
| EP-A-0104940 | 04-04-84 | AU-B- 544881 | 20-06-85 |
| | | AU-A- 1961883 | 05-04-84 |
| | | CA-A- 1273921 | 11-09-90 |
| | | GB-A, B 2127817 | 18-04-84 |
| | | JP-A- 59080670 | 10-05-84 |
| | | US-A- 4569690 | 11-02-86 |
| | | US-A- 4675044 | 23-06-87 |
| ----- | | | |
| EP-A-0363316 | 11-04-90 | AU-B- 629854 | 15-10-92 |
| | | AU-A- 4169989 | 05-04-90 |
| | | ES-T- 2045545 | 16-01-94 |
| | | JP-A- 2243609 | 27-09-90 |
| | | NO-C- 173723 | 26-01-94 |
| | | US-A- 5284844 | 08-02-94 |
| ----- | | | |